



1. NOME DELLA SOSTANZA O MISCELA E DELL'AZIENDA

1. IDENTIFICATION OF THE MIXTURE AND OF THE COMPANY/UNDERTAKING

1.1. Informazioni sul prodotto | Product identifier

Nomi commerciali | Trade Name:

VAICO DCTF 2

VAICO Nr. | VAICO No.:

V60-0487, V60-0488, V60-0489, V60-0490, V60-0491, V60-0492

1.2. Produttore/Fornitore | Informing department

VIEROL AG | Karlstraße 19 | 26123 Oldenburg | Germany

Telefon +49 441 - 210 20-0 | Telefax +49 441 - 210 20-111

2. CARATTERISTICHE | PROPERTIES

Sviluppato appositamente per la terza generazione di DCT di Magna GETRAG con frizione a bagno d'olio. Garantisce prestazioni eccezionali della frizione e stabilità dell'attrito per l'intera durata di vita e quindi un elevato livello di comfort di cambiata durante la guida.

Specially developed for the third DCT generation from Magna GETRAG with oil bath clutch. Ensures outstanding clutch performance and friction stability over the entire service life and thus a high level of shifting comfort while driving. Use in accordance with the manufacturer's instructions. Safety data sheet available on request.

3. DESCRIZIONE DEL SERVIZIO | PERFORMANCE DATA

3.1. Raccomandazione* | Recommendations*:

BMW 83 22 2 433 157 (DCTF 2) | **Mercedes-Benz** 239.21, 236.24, 236.25 | **FORD** WSS-M2C218-A1 (F-DC) |

RENAULT 77 11 785 243 (DW5) | **PORSCHE** 043 207 29, 043 207 30, 000 043 20, 000 043 305 13, 999 917 080 00, 999.917.080.01, 000 043 210 44, 971 094 307 02A

CARATTERISTICHE TIPICHE TYPICAL VALUES	METODI METHOD	UNITÀ UNIT	VAICO DCTF 2
Densità a 15° C Density at 15° C	DIN 51 757	kg/m ³	847
Viscosità a 40° C Viscosity at 40° C	DIN 51 562	mm ² /s	36
Viscosità a 100° C Viscosity at 100° C	DIN 51 562	mm ² /s	7
Viscosità a -40° C Viscosity at -40° C	DIN 51 938	mPa.s	< 18.000
Doppietto Pour point	DIN ISO 3016	° C	-45
Indice di viscosità (VI) Viscosity index (VI)	DIN ISO 2909	-	158
Punto d'inflammabilità Flash point	DIN ISO 2592	° C	> 200

* Soddisfa i requisiti del produttore OEM. I valori indicati possono variare entro i normali limiti commerciali.

* meets the requirements of the OEM manufacturer. The above values may vary within commercially accepted tolerances